

OG SERIES ONGLAZE METALLIC COLOURS (LEAD CONTAINING & LEAD FREE) FOR TABLEWARE, EARTHENWARE, STONEWARE, PORCELAIN, BONE CHINA & TILE

The Colour Chart shows an approximate impression of the basic colours for a first selection of colours. For exact reproduction of a colour tone it is absolutely necessary to test a sample under original conditions.



Please Note:

The information in this leaflet are based on our current knowledge and experience. This description does not release the users from examinations and tests of their own because of uncountable possible influences, when using and applying the products in connection with every other material being involved in the production. It can not be deduced a legally obliged assurance for specific characteristics or for the aptitude of a definite usage purpose. The receiver of our products has to observe by his own responsibility probable protecting rights as well as existing laws, rules and regulations.

OG SERIES ONGLAZE METALLIC COLOURS (LEAD CONTAINING & LEAD FREE) FOR TABLEWARE, EARTHENWARE, STONEWARE, PORCELAIN, BONE CHINA & TILE

TECHNICAL DATA SHEET AND USAGE

The OG Series are metallic colours for Onglaze or Third Fire application . Two product ranges are available, one lead-containing and one lead-free. The colours can be used on Lead Free substrates and glazes and had been designed for maximum miscibility and optimal metal release.

MAIN PROPERTIES

High color intensity

The highest intensity is obtained by printing the colors without flux addition. Gloss and intensity can be fine-tuned by adding a higher or lower amount of flux.

Leaded Group	PE-1114-C
Unleaded Group	ULE-1441-C

Excellent particle size powder distribution

The particle size of the colors will vary depending on the composition, in this series the Typical Diameter particle D90=60 microns.

Very good resistance

Mechanical durability is widely resistant showing good resistance, however, it is necessary for users to determine metal release and durability, according to their own production conditions.

Low thermal expansion coefficient

The Coefficients of thermal expansion are suitable for different materials:

Leaded Group	$75-85 \times 10^{-7} \cdot 1/K$ (20 to 400°C)
Unleaded Group	$70-80 \times 10^{-7} \cdot 1/K$ (20 to 400°C)

MISCIBILITY AND COMPATIBILITY

All colours are designed for maximum intermixing.

APPLICATION

DIRECT SCREEN PRINTING AND DECALS

For screen printing directly or for decal transfers a 48T polyester mesh is recommended.

On substrate such as hard and soft paste porcelain with a lower co-efficient of thermal expansion the recommended permitted layer thickness should not exceed 20 microns in order to avoid cracking or flaking of the enamels and must be observed where several layers are built up or applied or one thick layer, customers must assess suitability including re-fired pieces, thicker layers are possible on vitreous bodies, Bone China, etc.

Please Note:

The information in this leaflet are based on our current knowledge and experience. This description does not release the users from examinations and tests of their own because of uncountable possible influences, when using and applying the products in connection with every other material being involved in the production. It can not be deduced a legally obliged assurance for specific characteristics or for the aptitude of a definite usage purpose. The receiver of our products has to observe by his own responsibility probable protecting rights as well as existing laws, rules and regulations.

OG SERIES ONGLAZE METALLIC COLOURS (LEAD CONTAINING & LEAD FREE) FOR TABLEWARE, EARTHENWARE, STONEWARE, PORCELAIN, BONE CHINA & TILE

As a guide, recommended mixing ratios and mediums below:

Reference	Description	Parts medium per 10 parts of colour	Water Media	Oil-based Media
L427	WATER MISCIBLE MEDIUM	3,5	✓	
W172	WATERBASED PRINT MEDIUM	3,5	✓	
M286D	SEMI-THIXO S/PRINT MEDIUM	6		✓
M286T	THIXOTROPIC S/P MEDIUM	8		✓
M51D	SCREEN TRANSFER MEDIUM	5		✓
M6	DIRECT PRINT MEDIUM	3,5		✓

HANDPAINTING-MACHINE BANDING AND LINING & SPRAYING OR AEROGRAPHING

The colors can be supplied as dry powder for painting directly onto glazed ware and also in the following mediums:

Reference	Description	Parts medium per 10 parts of colour	Water Media	Oil-based Media
W108	WATERBASED HAND PAINT MEDIUM	6	✓	
M162N	GELLED BANDING MEDIUM	5		✓
M9	HAND PAINTING MEDIUM	3,5		✓

FIRING RECOMMENDATIONS

For cycles of 4 hours or more the following temperatures are recommended:

	Leaded Group	Unleaded Group
Hard Paste Porcelain	800 - 850 degrees	840-880 degrees
Soft Paste Porcelain	790 - 840 degrees	840-870 degrees
Vitreous Tableware	780 - 820 degrees	840-870 degrees
Bone China	780 - 820 degrees	820-850 degrees
Earthenware/Tiles	760 - 850 degrees	850-900 degrees

Fast firing and shorter cycles are possible:

850-880 degrees/60-90 min 860-900 degrees/60-90 min

Firing affects metal release and durability so it is best determined depending on cycle profile.

Please Note:

The information in this leaflet is based on our current knowledge and experience. This description does not release the users from examinations and tests of their own because of uncountable possible influences, when using and applying the products in connection with every other material being involved in the production. It can not be deduced a legally obliged assurance for specific characteristics or for the aptitude of a definite usage purpose. The receiver of our products has to observe by his own responsibility probable protecting rights as well as existing laws, rules and regulations.

OG SERIES ONGLAZE METALLIC COLOURS (LEAD CONTAINING & LEAD FREE) FOR TABLEWARE, EARTHENWARE, STONEWARE, PORCELAIN, BONE CHINA & TILE

ACID AND ALKALI RESISTANCE











The chemical resistance of the fired color layers is influenced by the color deposit, the firing conditions and the glaze. The colors could show a very slight visible attack with 4%acetic acid solution (22+-2°C, 24h) as well as with 5% sodium carbonate solution (60+-2°C, 32h). We recommend carrying out tests under industrial conditions.

METAL RELEASE CHARACTERISTICS (Leaded Group)

Every effort is made to manufactured these colors with the lowest metal release possible, there are in the order of typically less than 0.3% Lead and 0.03% Cadmium respectively under normal application conditions and optimal firing and experience show results well below current permissible limits for tableware.

Metal release conditions can be influenced by deposit weight, glaze composition, firing conditions (firing cycle and kiln atmosphere), etc. and, in general, the higher the cycle temperatures, the better metal release and greater durability will be obtained. Under some conditions, note that the lining of kilns previously used to fire Low-Sol or Lead products is known to release volatile metals detectable in the test.

REFERENCES

	Colour	Reference		Colour Composition
Leaded Group:		OG-1666-M	Metallic Gold	Si-Al-K-Fe-Ti
		OG-1667-T	Metallic Pearl	Si-Al-K-Ti
		OG-1668-M	Metallic Red	Si-Al-K-Fe
		OG-1916-R	Metallic Bronze	Si-Al-K-Fe-Ti
		OG-1917-T	Metallic Silver	Si-Al-K-Ti-Co-Cr
Unleaded Group:		OG-7001-T	Metallic Silver	Si-Al-K-Ti-Co-Cr
		OG-7002-M	Metallic Red	Si-Al-K-Fe
		OG-7003-R	Metallic Bronze	Si-Al-K-Fe-Ti
		OG-7004-H	Metallic Gold	Si-Al-K-Fe-Ti
		OG-7005-T	Metallic Pearl	Si-Al-K-Ti

Please Note:

The information in this leaflet are based on our current knowledge and experience. This description does not release the users from examinations and tests of their own because of uncountable possible influences, when using and applying the products in connection with every other material being involved in the production. It can not be deduced a legally obliged assurance for specific characteristics or for the aptitude of a definite usage purpose. The receiver of our products has to observe by his own responsibility probable protecting rights as well as existing laws, rules and regulations.